

Special Pipe – Spears® PVC Clear



Spears® PVC clear Schedule 40 or Schedule 80 piping provides optimum clarity for critical visual monitoring of processes fluids. Joined using standard solvent cement welding with clear cement, clear systems provide the many benefits of regular PVC, such as excellent corrosion resistance, smooth interior walls, non-contaminating, non-conductive, light weight, good pressure handling capacity, superior impact strength and does not support bacterial growth.

A supplemental line of 1/4" through 12" Spears® PVC clear fittings are available. Socket-style fittings are manufactured in strict dimensional compliance with ASTM D 2466 to Schedule 40 requirements. Spears® Special Reinforced Plastic Thread (SR) female threaded transition fittings, incorporating a stainless steel retaining ring, reduce problems associated with over tightening and provide a strong, leak-tight seal for plastic-to-metal transitions. Specialty transition fittings are manufactured to Schedule 80 dimensions per the applicable requirements of ASTM D 2467. See Spears® Schedule 40 or Schedule 80 fitting weight and dimension publications for available sizes and configurations. Spears® PVC clear can be easily installed with systems of regular PVC pipe, fittings and valves. In addition, an endless selection of fully compatible PVC components and accessories are readily available.

Material

Spears® PVC clear piping is produced from a rigid, lead-free virgin Polyvinyl Chloride (PVC) compound with superior impact resistance and a maximum service temperature of 140°F when appropriate temperature/pressure de-rating factors are applied. Spears® PVC clear materials are certified by the NSF International for use with potable water under ANSI/NSF® Standard 61 and acceptable for food contact under the provisions of Title 21 of the United States FDA Code of Federal Regulations. Spears® PVC clear piping also exhibits excellent flammability characteristics and will not sustain combustion when flame source is removed.

Spears® PVC clear provides the excellent chemical resistance properties of PVC piping. It is resistant to most acids, bases, salts and oxidants. PVC chemical resistance data should be referenced for proper application. Although this material maintains its physical properties when exposed to many substances, exposure to certain chemicals can affect the clarity of the product over time. Certain nitrogen containing organics, bleaches, oxidative agents and acids may result in discoloration. Testing under actual use conditions is recommended. Exposure to sunlight (Ultra Violet Radiation) will also affect clarity. Clear products do not contain UV stabilizers and are not recommended for outdoor use unless adequate protection is applied.

Clear PVC Pipe Physical Properties		
GENERAL	Value	Test Method
Cell Classification	12454	ASTM D 1784
Maximum Service Temp.	140°F	
Color	Transparent	
Specific Gravity, (g/cu.cm @ 73°F)	1.33	ASTM D 792
Hardness, Shore D	84	ASTM D 2240
Hazen-Williams Factor	C = 150	
MECHANICAL		
Tensile Strength, psi @ 73°F	7,260	ASTM D 638
Tensile Modulus of Elasticity, psi @ 73°F	392,000	ASTM D 638
Flexural Strength, psi @ 75°F	12,000	ASTM D 790
Flexural Modulus, psi @ 75°F	389,000	ASTM D 790
Compressive Strength, psi @ 75°F	8,300	ASTM D 695
Compressive Modulus, psi @ 75°F	307,000	ASTM D 695
Notched Izod Impact - .125" Injection Molded	23 ft.-lbs./in.	ASTM D 256
Notched Izod Impact - .125" With Flow-Comp. Molded	8.0 ft.-lbs./in.	ASTM D 256
Notched Izod Impact - .125" Cross Flow-Comp. Molded	2.0 ft.-lbs./in	ASTM D 256
THERMAL		
Coefficient of Linear Expansion (in/in/°F)	4.1 x 10 ⁻⁵	ASTM D 696
Heat Distortion Temp., 264 psi, .125 in. Bars	154°F	ASTM D 648
Glass Transition Temp.	176°F	
FIRE PERFORMANCE		
Flammability Rating	V-0	UL-94



Special Pipe – Spears® PVC Clear

Schedule 40 Dimensions

Nom. Pipe Size (in.)	O.D.	Average I.D.	Min. Wall	Nom. Wt./Ft.	Max. W.P. PSI
1/4	0.540	0.344	0.088	0.086	390
3/8	0.675	0.473	0.091	0.115	310
1/2	0.840	0.602	0.109	0.170	300
3/4	1.050	0.804	0.113	0.226	240
1	1.315	1.029	0.133	0.333	220
1-1/4	1.660	1.360	0.140	0.450	180
1-1/2	1.900	1.590	0.145	0.537	170
2	2.375	2.047	0.154	0.720	140
2-1/2	2.875	2.445	0.203	1.136	150
3	3.500	3.042	0.216	1.488	130
3-1/2	4.000	3.521	0.226	1.789	120
4	4.500	3.998	0.237	2.118	110
6	6.625	6.031	0.280	3.73	90
6-1/2	6.625	6.335	0.110	1.64	45
8	8.625	7.942	0.322	5.619	80
10	10.750	9.976	0.365	7.532	70

Schedule 80 Dimensions

Nom. Pipe Size (in.)	O.D.	Average I.D.	Min. Wall	Nom. Wt./Ft.	Max. W.P. PSI
1/4	0.540	0.282	0.119	0.105	570
3/8	0.675	0.403	0.126	0.146	460
1/2	0.840	0.526	0.147	0.213	420
3/4	1.050	0.722	0.154	0.289	340
1	1.315	0.936	0.179	0.424	320
1-1/4	1.660	1.255	0.191	0.586	260
1-1/2	1.900	1.476	0.200	0.711	240
2	2.375	1.913	0.218	0.984	200
3	3.500	2.864	0.300	2.010	190
4	4.500	3.786	0.337	2.938	160
6	6.625	5.709	0.432	5.610	140

De-Rating Factor

Operating Temp (°F)	De-Rating Factor
73	1.00
80	0.88
90	0.75
100	0.62
110	0.51
120	0.40
130	0.31
140	0.22

EX: 4" PVC SCHEDULE 40 CLEAR @ 120°F = ?
 110 psi x 0.40 = 44 psi max. @ 120°F

Critical Collapse Pressure PSI @ 73°F

Pipe Size (in.)	SCH 40	SCH 80
1/4	7,504	22,172
3/8	3,714	11,869
1/2	3,255	9,370
3/4	1,722	4,985
1	1,399	3,841
1-1/4	767	2,158
1-1/2	554	1,599
2	327	1,014
2-1/2	431	1,176
3	279	809
3-1/2	211	632
4	169	521
6	84	333
8	57	-
10	43	-

THE MAXIMUM SERVICE TEMPERATURE FOR PVC CLEAR IS 140°F.

Threading of Schedule 40 PVC Clear pipe is not a recommended practice due to insufficient wall thickness.

Joining Methods

Spears® PVC Clear pipe is easily joined by standard solvent cementing process, threaded connections and flanges. To maintain system clarity, Spears® recommends the use of a clear, medium-bodied, fast-setting cement in conjunction with a clear primer for optimum joint integrity. See Installation section for industrial pressure pipe for guidelines.

Thermal Expansion and Contraction

Standard calculations for thermal expansion and contraction may be applied to Spears® PVC clear. The coefficient of linear expansion for Spears® Clear pipe is 4.1×10^{-5} in./in./°F. The rate of expansion or contraction can be calculated as follows:

$$\Delta L = 12 yL (\Delta T)$$

Where:

ΔL = expansion or contraction in inches

$y = 4.1 \times 10^{-5}$ (coefficient of linear expansion)

L = length of piping run in feet

T = temperature change °F ($T_{max} - T_{@ installation}$)

Hangers and Supports

Spears® PVC clear piping should be mounted and supported in the same manner as PVC industrial piping. Support location and spacing are based on the pipe diameter, operating temperature of the system, and the location of any concentrated stress loads (i.e., valves, flanges, and any other heavy system components). As with regular PVC piping, hangers used must have an adequate load-bearing surface free of any rough or sharp edges that could damage the piping during use. They must also not restrict linear movement of the system due to the effects of expansion and contraction; over tightening must be avoided. See Hangers and Supports section for industrial pressure pipe for additional information.